



KÖSTER Joint Sealant FS-H grey

Technical Data Sheet J 234

Issued: 2019-09-06

Off. Test Certificate, OMTL, Hanover – resistance to diesel oil

Self-levelling, elastic 2 component polysulphide joint sealant

	<p>KÖSTER BAUCHEMIE AG Dieselstraße 1-10, 26607 Aurich 17 J 231 EN 14188-2 Grey KÖSTER Joint Sealant FS-H Cold applied jointing material for streets, bridge decks, parking lots, etc.</p>
Adhesion and elongation capacity	Modulus of tension at 100% elongation at + 23 °C ≥ 0.15 MPA at - 20 °C ≤ 0.6 MPA
Adhesion capacity	no failure at - 20 °C ≤ 0.6 MPa
Water impermeability	Modulus of tension at 100% elongation at + 23 °C ≥ 0.15 MPA at - 20 °C ≤ 0.6 MPA No failure at -20 °C ≤ 0.6 MPa
Resistance to deflection	Resilience ≥ 70% Volume loss ≤ 5%
Durability of water impermeability under chemical attack	Passed
Durability of all mandated properties against aging	Change in modulus of tension at 100% elongation ≤ +/- 20%
Resistance to flames	Passed

Features

KÖSTER Joint Sealant FS-H is a polysulphide based elastic, pourable joint sealant in accordance with DIN 18540 for sealing joints in horizontal areas. When fully cured, KÖSTER Joint Sealant FS-H is a rubbery elastic sealant with a high mechanical load capacity, good resistance to UV radiation, water, sea water, salt solutions, benzenes, and mineral oils. It is root resistant, does not rot, and it has very good retraction properties.

Technical Data

Color	light grey
Mixing ratio by weight	100 : 8 (A : B)
Pot life	approx. 2 hours (+ 20 °C, 50 % rel. hum.)
Curing time	approx. 24 hours (+ 23 °C, 50 % rel. hum.)
Consistency	pourable, self-levelling
Specific gravity	approx. 1.65 kg / l
Shore A-hardness	approx. 35
Retraction capacity	≥ 80 %
Total deformation permitted	approx. 25 %
Application temperature	+ 5 °C to + 40 °C
Max. application slope	2 %

Fields of Application

KÖSTER Joint Sealant FS-H can be used to permanently and elastically seal horizontal joints in below grade construction, cracks in basements, foundations of buildings, joints in sewage treatment plants, garages, tunnels, etc.

Application

The flanks of the joints have to be clean, solid, and free of grease and dust. Substrates must be primed with KÖSTER FS-Primer 2C. Mix both components thoroughly using a slow speed mixer until a homogeneous consistency is reached, (at least 3 minutes). The joint is filled approx. 2 hours after priming by pouring or with a caulking gun and is smoothed with a trowel or spatula.

Consumption

Approx. 1.6 kg / l void						
Joint width in mm	10	15	20	25	30	35
Thickness of joint sealant (in mm)	8	10	12	15	18	20
Deviation allowed (in mm)	+/-2	+/-2	+/-2	+/-3	+/-3	+/-4
Distance of joints allowed in m	2-4	2-6	4-7	5-8	6-9	7-10
Consumption kg / m	0.13	0.25	0.40	0.62	0.89	1.10

Cleaning

Clean tools immediately after use with KÖSTER Universal Cleaner.

Packaging

J 234 004 4 kg combipackage

Storage

Store the material dry and frost free. In originally sealed packages it can be stored for a minimum of 6 months.

Safety

Wear safety gloves and goggles when working with the material. Observe all governmental, state, and local safety regulations while processing the material.

Related products

KÖSTER FS Primer 2C	Prod. code J 139 200
KÖSTER Joint Sealant FS-V black	Prod. code J 231

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The proper and thereby effective and successful application of our products is not subject to our control. The installer is responsible for the correct application under consideration of the specific conditions of the construction site and for the final results of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which exceed the specifications contained in this technical guideline require written confirmation. The valid standards for testing and installation, technical guidelines, and acknowledged rules of technology have to be adhered to at all times. The warranty can and is therefore only applied to the quality of our products within the scope of our terms and conditions, not however, for their effective and successful application. This guideline has been technically revised; all previous versions are invalid.

KÖSTER Joint Sealant FS-H black
KÖSTER Joint Sealant FS-V grey
KÖSTER Universal Cleaner

Prod. code J 232
Prod. code J 233
Prod. code X 910 010

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The proper and thereby effective and successful application of our products is not subject to our control. The installer is responsible for the correct application under consideration of the specific conditions of the construction site and for the final results of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which exceed the specifications contained in this technical guideline require written confirmation. The valid standards for testing and installation, technical guidelines, and acknowledged rules of technology have to be adhered to at all times. The warranty can and is therefore only applied to the quality of our products within the scope of our terms and conditions, not however, for their effective and successful application. This guideline has been technically revised; all previous versions are invalid.

KÖSTER BAUCHEMIE AG • Dieselstraße 1-10 • D-26607 Aurich • Tel. 04941/9709-0 • Fax -40 • info@koester.eu • www.koester.eu